


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29D 7/01	A1	(11) International Publication Number: WO 99/67081 (43) International Publication Date: 29 December 1999 (29.12.99)
<p>(21) International Application Number: PCT/US99/13837</p> <p>(22) International Filing Date: 22 June 1999 (22.06.99)</p> <p>(30) Priority Data: 09/103,951 24 June 1998 (24.06.98) US</p> <p>(71) Applicant: TREDEGAR CORPORATION [US/US]; 1100 Boulders Parkway, Richmond, VA 23225 (US).</p> <p>(72) Inventors: PELKIE, James, E.; 121 Country Club Road, Terre Haute, IN 47803 (US). RIEKER, Gregory, M.; 16019 S. Zellwood Drive, Clinton, IN 47842 (US).</p> <p>(74) Agents: BACON, Jeffery, E. et al.; Jenkins & Gilchrist, P.C., 3200 Fountain Place, 1445 Ross Avenue, Dallas, TX 75202-2799 (US).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>

(54) Title: STRETCHABLE FILM HAVING ELONGATED APERTURES



(57) Abstract

Elongated apertures (14) each having a major axis (16) and a minor axis (18), are formed in a stretchable film (10) having a predefined direction of stretch (S). The apertures are oriented in the film with the major axes (16) of the apertures disposed perpendicular to the predefined direction of stretch (S). The apertures (14) are also disposed in the film with greater separation (A) between the apertures (14) in the direction parallel to the major axes (16) of the apertures than the separation (B) between adjacent apertures (14) in a direction parallel to the minor axes (18) of the apertures (14). The elongated openings, when positioned with the major axes (16) perpendicular to a predefined direction of stretch (S), has better breathability and elastic properties than comparable symmetric aperture shapes when both are subjected to stretch.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

STRETCHABLE FILM HAVING ELONGATED APERTURES

BACKGROUND OF THE INVENTION

Technical Field

5 This invention relates generally to an apertured film product, and more particularly to an apertured elastomeric film that is stretchable in a predefined direction.

History of Related Art

10 Apertured elastomeric films are commonly used to impart elastic properties and breathability to personal hygiene articles, such as diapers, adult incontinence products, feminine hygiene products, medical wraps and the like. When an apertured film is stretched, the individual holes, or apertures, tend to collapse, and the amount of air or fluid that can pass through the film is reduced. A symmetrical hole will tend to collapse due to film necking-in across the direction of stretch. As a result, apertured films having a symmetrical hole shapes have a reduced open area when stretched. This characteristic restricts the transfer of moisture or liquid through the film, thereby reducing the effectiveness and comfort of the personal hygiene article.

15 Furthermore, apertured films having symmetrical hole shapes and pattern, i.e., equally spaced apart symmetrical openings, have the same cross-sectional area in all directions of stretch. Thus, the change in elastic properties, due to the presence of apertures in the film, are omni-directional, that is, the change in elastic properties in the direction of stretch attributable to the apertures are not any better than the change in elastic properties of the film resulting from the apertures in any other direction of stretch.

20 The present invention is directed to overcoming the problems set forth above. It is desirable to have an apertured elastomeric film that can be stretched in a predefined direction which maintain better breathability, i.e., porosity, under

25

elongation than symmetrically shaped holes or non-symmetrically shaped holes that do not have a short access aligned with the predefined direction of stretch. It is also desirable to have an apertured film, suitable for use in personal hygiene articles, that provides higher extension, and better elastic performance in the direction of stretch, than a film having a symmetrical pattern, while maintaining comparable open area in a relaxed state and less loss of open area in an elongated state.

SUMMARY OF THE INVENTION

In one aspect of the present invention, an apertured elastomeric film that is stretchable in a predefined direction, has a plurality of elongated apertures which have a major axis extending along the length of the respective aperture, and a minor axis transversely disposed with respect to the respective major axis. The major axis of each of the elongated apertures is orthogonally oriented with respect to the predefined direction of stretch.

Other features of the apertured elastomeric film embodying the present invention, include the film having a porosity, as measured by the flow rate of air through the film per unit area, when a 50% strain is applied to the film in the predefined direction of the stretch, that is at least 70% of the porosity of the film when in a relaxed state.

Other features of the apertured elastomeric film include the ratio of the length of the major axis to the length of the minor axis of each of the apertures being from about 1.5:1 to about 5.0:1. Additional features include the spacing between the apertures, in a direction parallel to the major axis of the apertures being less than the length of the major axis, and the spacing between apertures in a direction parallel to the minor axis of the apertures, being less than the length of the minor axis.

Yet other features of the apertured elastomeric film embodying the present invention include the spacing between the apertures, in a direction parallel to the major axes of the apertures, being from about 1.5 to about 5 times the spacing between the apertures in a direction parallel to the minor axes of the apertures.

In another aspect of the present invention, an apertured elastomeric film that is stretchable in a defined direction and has a plurality of elongated apertures extending

through the film, has a porosity as measured by the flow rate of air through the film per unit area, when a 50% strain is applied to the film in a predefined direction of stretch, of at least 70% of the porosity of the film when in a relaxed state.

Other features of the apertured elastomeric film include each of the apertures having a major axis extending along the length of a respective aperture and a minor axis transversely disposed with respect to the major axis, wherein the major axis of each of the elongated apertures is orthogonally oriented with respect to the predefined direction of stretch.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete understanding of the structure and operation of the present invention may be had by reference to the following detailed description when taken in conjunction with the accompanying drawings, wherein:

FIG. 1 is a plan view of a stretchable apertured film embodying the present invention, with a portion of the apertures shown in enlarged detail for clarity;

FIG. 2 is a schematic representation an illustrative embodiment of a hole pattern embodying the present invention;

FIG. 3 is a schematic representation of another illustrative embodiment of another hole pattern embodying the present invention; and

FIG. 4 is a schematic representation of still another illustrative embodiment of yet another hole pattern embodying the present invention.

DETAILED DESCRIPTION OF PRESENTLY PREFERRED EXEMPLARY EMBODIMENTS

Apertured elastomeric films are commonly used to provide transmission of moisture and fluid, for example between an area adjacent a skin surface and an absorptive layer, in personal hygiene articles such as diapers, adult incontinence products, and feminine hygiene products. The elastomeric films in such products, may be stretched from about 50% to about 200% during use in disposable articles such as diapers. Heretofore, there has been a significant loss in the porosity of the apertured film when stretched, due to collapse of the holes and necking-in across the direction of stretch, and the resultant loss in open area.

In the preferred embodiment of the present invention, as shown in Fig. 1, an apertured elastomeric film 10, has the plurality of elongated apertures 14 formed therethrough. Preferably, the elastomeric film 10 is formed of a thermoplastic material in which the apertures 14 are produced by vacuum forming, hydroforming, or other method in which the film is simultaneously perforated and shaped. For example, a method of producing a perforated film is described in U.S. Patent 5,718,928, issued February 7, 1998, titled "*Screen For Producing A Perforated Film*", to Gregory M. Rieker, a co-inventor of the invention described herein and assigned to the assignee of the present invention. While any one of several thermoplastic materials may be used to form the initial base structure for the apertured film 10 embodying the present invention, in practice it has been found that polyolefin materials and other thermoplastic elastomeric materials including styrene block copolymers, polyurethane, ethylene vinyl acetate, and the like, work particularly well in forming the stretchable apertured film with specifically aligned elongated openings in accordance with the present invention.

As best illustrated in Figs. 2-4, each of the apertures 14 have a major axis 16, extending along the length of the aperture, and a minor axis 18 extending across the width of each of the apertures 14. In Figs. 2-4 and in the tables presented below, the length of the major axis 16 of each of the apertures 14 is designated by the letter X, and the length of the minor axis 18 of each aperture 14 is designated by the letter Y.

Major-to-minor axis ratios, i.e., ratios of X:Y, of from about 1.5:1 to about 5:1 are preferred to achieve the desired performance with elastomeric films that are stretched 50% to 200% in a predefined direction S, as indicated in Fig. 1, during use in disposable articles such as diapers. Importantly, the major axis 16 of each of the apertures 14 is orthogonally oriented with respect to the predefined direction of stretch S, i.e., the minor axis 18 of each of the apertures is aligned parallel to the predefined direction of stretch S.

Also, as illustrated in Figs. 2-4, the separation between the apertures 14 in the direction of the major axis 16 is designated as dimension A, and the dimension separating the apertures 14 in the direction of the minor axis 18 is designated by the letter B. Ratios of from about 1.5:1 to about 5:1 are preferred for the respective separation distances between holes 14 in the respective directions along the major 16 and minor axis 18.

The orientation of the elongated openings 14, with respect to a predefined direction of stress S, is extremely important in carrying out the present invention. With the minor axis 18 of the apertures 14 oriented parallel with the direction of stress S, when a tensile force is applied in a predefined direction S, the elongated openings 14 tend to assume a more symmetric shape. For example, an oval shape tends to become circular when the film 10 is stretched in a direction perpendicular to the major axis 16. This characteristic is important in reducing the loss of porosity as a tensile force is applied in the predefined direction of stretch S.

As listed in Table I, eight different films were vacuum formed and tested in accordance with ASTM D-737. The aperture sizes and open areas, as measured on the screen on which the films were formed, is listed below in Table I. The actual aperture size and open area of the test films was slightly less than the listed dimensions and open area percentages of the measured screens, due to the thickness of the formed films (about 0.003"). However, it is believed that the dimensional and open area properties are substantially equally reduced for all the samples and the resultant porosity properties equally affected.

TABLE I

PARAMETER	RATIO X:Y				
	2:1	3:2	3:1	4:1	5:1
X axis length (mm)	0.76	0.76	2.29	2.03	2.54
Y axis width (mm)	0.38	0.51	0.76	0.51	0.51
A land length (mm)	0.63	0.63	1.52	2.29	1.78
B land width (mm)	0.32	0.32	0.38	0.32	0.33
Screen open area	23%	26%	31%	23%	29%

Square holes (in a 90° array)

62 holes per square area

X axis length 0.63 mm

Y axis width 0.63 mm

A land length 0.63 mm

B land width 0.63 mm

Screen open areas 25%

Circular holes (in a 60° array)

112 holes per square cm

hole diameter 0.58 mm

Screen open area 30%

Hexagonal holes (in a 60° array)

13.6 holes per square cm

Long axis 1.75 mm

Across flats 1.52 mm

Screen open area 27%

Table II, below, demonstrates the effect of hole shape on the porosity of variously-shaped apertured elastic films, when subjected to varying amounts of tensile strain, i.e., stretch, a direction perpendicular to the major axes of the openings. Air flow was repeatedly measured across a 1.5 inch diameter sample of each of the films identified in Table I. The square and round holes are geometrically symmetrical in shape opening, whereas the hexagonal holes have an axis that is somewhat longer than the distance across the flats of the hexagonal shape. Five different oval-shaped elongated apertures were tested, having X:Y ratios from 2:1 to 5:1.

As shown in Table II, the air flow through each test sample when the sample

was in a relaxed state, i.e., 0% elongation, was considered to be the 100% base for the subsequently measured air flow as the test sample was stretched to 100% elongation in a direction perpendicular to the major axes **16** of the elongated openings, in a direction perpendicular to the sides of the square openings, and diametrically with respect to the round-shaped apertures. Porosity is defined as the volume of air flow per minute per unit area at a pressure drop of 0.5 inches (1.27 cm) of water. As can be seen from the test results, the square, round, and substantially symmetrical hexagonally-shaped apertures exhibited a measurable decrease in porosity at just 10% elongation, and porosity dropped significantly as elongation increased to 50% whereat the test of those samples was discontinued. In marked contrast, the porosity of the elongated holes oriented with the major axis **16** perpendicular to the direction of elongation, showed a significant increase under 10% elongation. Moreover, the apertures having a 3:1 to 5:1 ratio of major to minor axes (X:Y) not only showed an immediate increase in porosity under 10% elongation, but exhibited better porosity from 10% to 100% elongation than in the relaxed state (0% elongation). Significantly, the apertures having a 3:1 ratio of major to minor axes had double the initial porosity at 40% to 50% elongation, and almost double the porosity of the film in the relaxed state when stretched to 100% elongation.

TABLE II

Effect of Elongation on Porosity of Films with Various Hole Patterns								
Hole Pattern	ELONGATION							
	0%	10%	20%	30%	40%	50%	75%	100%
Square	100%	96%	87%	75%	57%	40%	--	--
Round	100%	93%	82%	72%	52%	47%	--	--
Hexagonal	100%	88%	74%	59%	52%	37%	--	--
2:1 Oval	100%	104%	96%	88%	83%	77%	--	--
3:2 Oval	100%	104%	95%	88%	81%	74%	--	--
3:1 Oval	100%	123%	149%	179%	200%	203%	193%	186%

20

Effect of Elongation on Porosity of Films with Various Hole Patterns								
Hole Pattern	ELONGATION							
	0%	10%	20%	30%	40%	50%	75%	100%
4:1 Oval	100%	109%	113%	116%	122%	127%	120%	112%
5:1 Oval	100%	110%	117%	120%	124%	122%	117%	115%

The above test demonstrates that there is significantly improved porosity for an apertured film having elongated holes, where the strain is applied in a direction perpendicular to the major axis of the elongated openings, when compared to an apertured film having symmetric openings. Furthermore, although the elongated apertures 14 may have other shapes, such as elongated rectangles or other multi-sided shapes, elliptical holes are preferred because there are no discontinuities, i.e., corners, that initiate or propagate tears during stretch.

In addition to the porosity advantages provided by an elongated aperture oriented with the major axis 16 of the aperture 14 perpendicular with a predefined direction of stretch S, the pattern of the elongated apertures 14 through the film can be arranged to provide higher extension forces and better elastic performance than that provided by a symmetrical pattern. This is accomplished while providing comparable open area in a relaxed state, and less loss of open area when stretched. In the present invention, this advantage is provided by arranging the apertures 14 so that there is greater separation, i.e., spacing, between apertures 14 in the direction of the major axis 16 than in the direction of the minor axis 18. In Table III, eleven exemplary embodiments of the present invention are presented. The ratios of the spacing A between the major axis 16 and the spacing B, between the minor axis 18 of each embodiment is listed. The ratio of dimension A to dimension B, varies from about 2:1 to 7:1. Furthermore, in the eleven examples presented, the length of the elongated apertures 14, that is, the distance X along the major axis 16 of the individual apertures 14 varies from 0.76mm to 2.54mm, whereas the width distance Y along the respective minor axes 16 of the apertures 14 varies from 0.38mm to 0.76mm. In the exemplary embodiments, the ratio of major axis 16 to minor axis 18 (X:Y) varies from about 2:1 to 5:1. Importantly, the wider separation along the major axes 16 provides an

effectively greater film cross section in the direction of stretch S, and hence provides greater extendibility when the film 10 is stretched perpendicular to the major axis 16. In addition to the examples illustrating variously-sized openings and spacing between openings, the number of apertures 14 per unit area varies from slightly over 20/cm² to over 100/cm².

TABLE III

Example	mm		Ratio X:Y	mm		Ratio A:B	Approx. Holes per cm ²
	X	Y		A	B		
1	0.76	0.51	3:2	0.63	0.32	2:1	103
2	0.76	0.38	2:1	0.63	0.32	2:1	86
3	0.76	0.38	2:1	0.76	0.38	2:1	87
4	1.02	0.51	2:1	0.76	0.25	3:1	75
5	1.02	0.51	2:1	0.51	0.38	4:3	75
6	1.02	0.51	2:1	0.76	0.25	3:1	75
7	1.27	0.63	2:1	0.76	0.25	3:1	56
8	2.03	0.51	4:1	2.29	0.33	7:1	28
9	2.29	0.76	3:1	1.52	0.38	4:1	23
10	2.54	0.51	5:1	1.78	0.33	5.4:1	28
11	2.03	0.51	4:1	1.27	0.33	4:1	36

In the above-described exemplary embodiments, the apertures 14 are elliptically shaped. However, it is easily seen that other patterns with respective long and short axes, where the long axes 16 is disposed perpendicular to the direction of stretch, will also be effective. For example, elongated hexagonal, octagonal, or rectangular aperture shapes would also provide an improvement in breathability when the film is stretched in a direction perpendicular to the orientation of the major axes 16.

In positioning the apertures 14 in the film 10, the elongated apertures 14 may be formed aligned rows and columns with the respective major axes 16 and minor axes 18 in respective common alignment. Alternatively, as shown in Fig. 3, the elongated

apertures may be positioned in columns in which the minor axes **18** are aligned, but the major axes **16** are disposed in offset rows wherein the major axes **16** are offset from the aperture **14** in adjacently disposed columns. In a similar manner, as illustrated in Fig. 4, the elongated apertures **14** may be positioned in aligned rows wherein the major axes **16** are in respective alignment, but the minor axes **18** are offset.

Although the present invention is described in terms of a preferred exemplary embodiment, with additional illustrative embodiments, describing variously sized and shaped apertures **14** and aperture spacing and alignments, those skilled in the art will recognize that changes in those sizes, shapes, spacing, alignments and in the ratios of the major axes **16** to the minor axes **18**, may be made without departing from the spirit of the invention. Such changes are intended to fall within the scope of the following claims. Other aspects, features and advantages of the present invention may be obtained from a study of this disclosure and the drawings, along with the appended claims.

CLAIMS

What we claim is:

1. An apertured elastomeric film that is stretchable in a predefined direction, said film having a plurality of elongated apertures formed therethrough, each of said elongated apertures having a major axis extending along the length of a
5 respective aperture and a minor axis transversely disposed with respect to the respective major axis, the major axis of each of said elongated apertures being orthogonally oriented with respect to said predefined direction of stretch.

2. An apertured elastomeric film, as set forth in Claim 1, wherein
10 the porosity of said film, as measured by the flow rate of air through said film per unit area, has a value when a 50% strain is applied to said film in said predefined direction of stretch that is at least 70% of the porosity of said film when in a relaxed state.

3. An apertured elastomeric film, as set forth in Claim 1, wherein
15 the ratio of the length of said major axis to the length of said minor axis of each of the apertures is from about 1.5:1 to about 5.0:1.

4. An apertured elastomeric film, as set forth in Claim 3, wherein
the ratio of the length of said major axis to the length of said minor axis of each of the apertures is about 3:1.

5. An apertured elastomeric film, as set forth in Claim 1, wherein
20 the spacing between said apertures, in a direction parallel to said major axes of the apertures, is less than the length of said major axes.

6. An apertured elastomeric film, as set forth in Claim 1, wherein
the spacing between said apertures, in a direction parallel to said minor axes of the apertures, is less than the length of said minor axes.

7. An apertured elastomeric film, as set forth in Claim 1, wherein the spacing between said apertures in a direction parallel to said major axes of the apertures, is from about 1.5 to about 5 times the spacing between said apertures in a direction parallel to said minor axes.

5 8. An apertured elastomeric film that is stretchable in a predefined direction and has a plurality of elongated apertures formed therethrough, has a porosity of said film, as measured by the flow rate of air through said film per unit area, when a 50% strain is applied to said film in said predefined direction of stretch being at least 70% of the porosity of said film when in a relaxed state.

10 9. An apertured elastomeric film, as set forth in Claim 8, wherein each of said elongated apertures has a major axis extending along the length of a respective aperture and a minor axis transversely disposed with respect to the respective major axis, the major axis of each of said elongated apertures being orthogonally oriented with respect to said predefined direction of stretch.

15 10. An apertured elastomeric film, as set forth in Claim 8, wherein the ratio of the length of said major axis to the length of said minor axis of each of the apertures is from about 1.5:1 to about 5.0:1.

20 11. An apertured elastomeric film, as set forth in Claim 10, wherein the ratio of the length of said major axis to the length of said minor axis of each of the apertures is about 3:1.

12. An apertured elastomeric film, as set forth in Claim 8, wherein the spacing between said apertures, in a direction parallel to said major axes of the apertures, is less than the length of said major axes.

13. An apertured elastomeric film, as set forth in Claim 8, wherein the spacing between said apertures, in a direction parallel to said minor axes of the apertures, is less than the length of said minor axes.

5 14. An apertured elastomeric film, as set forth in Claim 8, wherein the spacing between said apertures in a direction parallel to said major axes of the apertures, is from about 1.5 to about 5 times the spacing between said apertures in a direction parallel to said minor axes.




FIG. 1




FIG. 2




FIG. 3




FIG. 4

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 99/13837

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B29D7/01

According to international Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B29D A61F B65D B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	BE 420 288 A (INTERNATIONAL LATEX PROCESSES LIMITED) 31 March 1937 (1937-03-31) page 6, line 11 - line 13 page 13, line 14 - line 27 table at page 14; figure 8 ----	1-14
A	GB 1 110 051 A (SMITH & NEPHEW LIMITED) 18 April 1968 (1968-04-18) page 4, line 5 - line 9; figure 20 ----	1-14
A	US 4 414 970 A (BERRY PETER W) 15 November 1983 (1983-11-15) column 4, line 47 - column 5, line 50 -----	1-14

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

23 September 1999

04/10/1999

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentplan 2
NL - 2280 HV Dordrecht

Authorized officer

Patent document cited in search report		Publication date	Patent family member(s)		Publicat n. date
BE 420288	A		NONE		
GB 1110051	A		NONE		
US 4414970	A	15-11-1983	AT	11216 T	15-02-1985
			AU	544583 B	06-06-1985
			AU	7358081 A	04-02-1982
			CA	1174548 A	18-09-1984
			DK	335881 A	31-01-1982
			EP	0045592 A	10-02-1982
			GB	2081177 A, B	17-02-1982
			IE	51970 B	13-05-1987
			JP	57066752 A	23-04-1982
			NZ	197782 A	31-07-1985
			ZA	8105051 A	29-09-1982